

PALM INTRANET

Day : Tuesday
Date: 3/12/2002
Time: 13:18:39

Inventor Name Search Result

Your Search was:

Last Name = MEDOFF

First Name = MARSHALL

Application#	Patent#	Status	Date Filed	Title	Inventor Name
<u>08921807</u>	<u>5952105</u>	150	09/02/1997	POLY-COATED PAPER COMPOSITES	MEDOFF , MARSHALL
<u>08961863</u>	<u>5973035</u>	150	10/31/1997	CELLULOSIC FIBER COMPOSITES	MEDOFF , MARSHALL
<u>09290031</u>	<u>6258876</u>	150	04/09/1999	CELLULOSIC FIBER COMPOSITES	MEDOFF , MARSHALL
<u>09328277</u>	Not Issued	161	06/08/1999	POLY-COATED PAPER COMPOSITES	MEDOFF , MARSHALL
<u>09337580</u>	<u>6207729</u>	150	06/22/1999	TEXTURIZED CELLULOSIC AND LIGNOCELLULOSIC MATERIALS AND COMPOSITIONS AND COMPOSITES MADE THEREFROM	MEDOFF , MARSHALL
<u>09338209</u>	Not Issued	041	06/22/1999	TEXTURIZED FIBROUS MATERIALS FROM POLY-COATED PAPER AND COMPOSITIONS AND COMPOSITES MADE THEREFROM CROSS REFERENCE TO RELATED APPLICATIONS	MEDOFF , MARSHALL
<u>09417512</u>	Not Issued	061	10/14/1999	LOAD-BEARING SYSTEMS	MEDOFF , MARSHALL
<u>09593627</u>	Not Issued	093	06/13/2000	COMPOSITIONS OF TEXTURIZED FIBROUS MATERIALS	MEDOFF , MARSHALL
<u>09772593</u>	Not Issued	030	01/30/2001	CELLULOSIC AND LIGNOCELLULOSIC MATERIALS AND COMPOSITIONS AND COMPOSITES MADE THEREFROM	MEDOFF , MARSHALL
<u>09961799</u>	Not	019	09/24/2001	SYSTEM AND METHOD	MEDOFF ,

	Issued			FOR CONTROLLING ACCESS AND USE OF PRIVATE INFORMATION	MARSHALL
<u>29119454</u>	Not Issued	095	03/01/2000	PALLET DESIGN	MEDOFF, MARSHALL
<u>29151333</u>	Not Issued	030	11/12/2001	PALLET	MEDOFF, MARSHALL
<u>60283571</u>	Not Issued	020	04/13/2001	NETWORK BASED PRIVATE OFFERINGS	MEDOFF, MARSHALL

Inventor Search Completed: Search Completed: No Records to Display.

	Last Name	First Name
Search Another: Inventor	<input type="text" value="medoff"/>	<input type="text" value="marshall"/>
	<input type="button" value="Search"/>	

(To go back use Back button on your browser toolbar.)

Back to [PALM](#) | [ASSIGNMENT](#) | [OASIS](#) | [Home page](#)



US006207729B1

(12) **United States Patent**
Medoff et al.(10) Patent No.: **US 6,207,729 B1**
(45) Date of Patent: ***Mar. 27, 2001**(54) **TEXTURIZED CELLULOSIC AND LIGNOCELLULOSIC MATERIALS AND COMPOSITIONS AND COMPOSITES MADE THEREFROM**(75) Inventors: **Marshall Medoff, Brookline; Arthur Lagace, Newtonville, both of MA (US)**(73) Assignee: **Xyleco, Inc., Brookline, MA (US)**

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **09/337,580**(22) Filed: **Jun. 22, 1999****Related U.S. Application Data**

(63) Continuation-in-part of application No. 08/961,863, filed on Oct. 31, 1997, now Pat. No. 5,973,035.

(51) Int. Cl.⁷ **C09K 11/00; C08J 5/13; C08K 89/00; C08L 97/00; A01N 25/00**(52) U.S. Cl. **523/129; 524/13; 524/14; 524/76; 47/26; 47/65.5; 111/200; 424/405; 424/411; 424/413; 424/414; 424/94.1; 426/5; 428/364; 428/374**(58) Field of Search **523/129; 524/13; 524/14, 76; 47/26, 65.5; 111/200; 424/405, 411, 413, 414, 94.1; 426/5; 428/364, 374**(56) **References Cited****U.S. PATENT DOCUMENTS**

1,824,221 9/1931 Mason .
 2,516,847 8/1950 Boehm .
 2,658,828 11/1953 Patilloch .
 2,665,261 1/1954 Baker .
 2,757,150 7/1956 Heritage .
 3,516,953 6/1970 Wood .
 3,718,536 2/1973 Downs et al. .
 3,836,412 9/1974 Boustany et al. .
 3,943,079 3/1976 Hamed .
 4,112,038 9/1978 Garner .
 4,113,908 9/1978 Shinomura .
 4,204,010 5/1980 Kramm et al. .
 4,244,847 1/1981 Posiviata et al. .
 4,265,846 5/1981 Shen et al. .
 4,279,790 7/1981 Nakajima .
 4,318,351 3/1982 Munk .
 4,559,376 12/1985 Kubát .
 4,608,922 9/1986 Pöhl .
 4,632,170 12/1986 Pöhl .
 4,674,414 6/1987 Nülle et al. .
 4,717,742 1/1988 Beshay .
 4,738,723 4/1988 Frizzell et al. .
 4,746,688 5/1988 Bistak et al. .
 4,791,020 12/1988 Kokta .
 4,810,445 3/1989 Lamb, Sr. et al. .
 4,818,604 4/1989 Tock .
 4,874,095 10/1989 Warych .
 4,963,603 10/1990 Felegi, Jr. et al. .

5,064,692 11/1991 Hofmann et al. .
 5,084,135 1/1992 Brooks et al. .
 5,088,910 2/1992 Goforth et al. .
 5,096,046 3/1992 Goforth et al. .
 5,096,406 3/1992 Brooks et al. .
 5,100,545 3/1992 Brooks .
 5,100,603 3/1992 Neefe .
 5,124,519 6/1992 Roy et al. .
 5,137,668 8/1992 Lamb, Sr. .
 5,155,147 10/1992 Doetz et al. .
 5,194,461 3/1993 Bergquist et al. .
 5,213,021 5/1993 Goforth et al. .
 5,254,617 10/1993 Inoue et al. .
 5,268,074 12/1993 Brooks et al. .
 5,277,758 1/1994 Brooks et al. .
 5,284,610 2/1994 Tai .
 5,285,973 2/1994 Goforth et al. .
 5,298,105 3/1994 Pohl .
 5,351,895 10/1994 Brooks et al. .
 5,366,790 11/1994 Liebel .
 5,372,878 12/1994 Saito .
 5,380,180 1/1995 Lamb, Sr. .
 5,421,205 6/1995 Pohl .
 5,437,766 8/1995 Van Phan et al. .
 5,439,542 8/1995 Liebel .
 5,441,801 8/1995 Deaner et al. .
 5,480,602 1/1996 Nagaich .
 5,486,553 1/1996 Deaner et al. .
 5,516,472 5/1996 Laver .
 5,539,027 7/1996 Deaner et al. .
 5,540,244 7/1996 Brooks et al. .
 5,543,205 8/1996 Liebel .

(List continued on next page.)

FOREIGN PATENT DOCUMENTS

47811/90 1/1989 (AT) .
 0 161 766 A1 11/1985 (EP) .
 60-168611 9/1985 (JP) .
 63-033440 2/1988 (JP) .
 63-033441 2/1988 (JP) .
 63-033442 2/1988 (JP) .
 63-033448 2/1988 (JP) .
 WO 96/13468 5/1996 (WO) .
 WO 96/13551 5/1996 (WO) .
 WO 97/18173 5/1997 (WO) .
 WO 99/11453 3/1999 (WO) .

OTHER PUBLICATIONS

Abstract of JP 09213296, filed Feb. 5, 1996, in Chemical Abstracts 127:223004.

Abstract of JP 09267441, filed Oct. 14, 1997, in Chemical Abstracts 127:294599.

Abstract of (Doctorate) Dissertation Abstract Int. B1988, 58(9), 4962 (published in Sep. 1997), in Chemical Abstracts 128:128805.

Primary Examiner—Nathan M. Nutter

(74) Attorney, Agent, or Firm—Fish & Richardson P.C.

(57) **ABSTRACT**

Texturized cellulosic or lignocellulosic materials, and compositions and composites made therefrom, are disclosed.

37 Claims, 1 Drawing Sheet

U.S. PATENT DOCUMENTS

5,558,933	9/1996	Anthony .	5,824,246	10/1998	Reetz .
5,574,094	11/1996	Malucelli et al. .	5,827,607	10/1998	Deaner et al. .
5,582,682	12/1996	Ferretti .	5,851,469	12/1998	Muller et al. .
5,643,359	7/1997	Soroushian et al. .	5,932,334	8/1999	Deaner et al. .
5,643,635	7/1997	Ahn et al. .	5,948,524	9/1999	Seethamraju et al. .
5,746,958	5/1998	Gustafsson et al. .	5,973,035 *	10/1999	Medoff et al. 524/13
5,759,680	6/1998	Brooks et al. .	6,004,668	12/1999	Deaner et al. .
5,767,177	6/1998	Omente et al. .	6,015,611	1/2000	Deaner et al. .
5,819,491	10/1998	Davis .	6,015,612	1/2000	Deaner et al. .

* cited by examiner



FIG. 1

1

TEXTURIZED CELLULOSIC AND LIGNOCELLULOSIC MATERIALS AND COMPOSITIONS AND COMPOSITES MADE THEREFROM

CROSS REFERENCE TO RELATED APPLICATIONS

This application is a continuation-in-part of U.S. patent application Ser. No. 08/961,863, filed Oct. 31, 1997 and now U.S. Pat. No. 5,973,035.

BACKGROUND OF THE INVENTION

The invention relates to texturized cellulosic or lignocellulosic materials and compositions and composites made from such texturized materials.

Cellulosic and lignocellulosic materials are produced, processed, and used in large quantities in a number of applications. Once used, these materials are usually discarded. As a result, there is an ever-increasing amount of waste cellulosic and lignocellulosic material.

SUMMARY OF THE INVENTION

In general, the invention features texturized cellulosic or lignocellulosic materials and compositions and composites made therefrom.

In one embodiment, the invention features a process for preparing a texturized fibrous material. The process involves shearing a cellulosic or lignocellulosic material having internal fibers (e.g., flax; hemp; cotton; jute; rags; finished or unfinished paper, paper products, or byproducts of paper manufacturing such as pulp board; or synthetic cellulosic or lignocellulosic materials such as rayon), to the extent that the internal fibers are substantially exposed, resulting in texturized fibrous material. The cellulosic or lignocellulosic material can be a woven material such as a woven fabric, or a non-woven material such as paper or bathroom tissue. The exposed fibers of the texturized fibrous material can have a length/diameter (L/D) ratio of at least about 5 (at least about 5, 10, 25, 50, or more). For example, at least about 50% of the fibers can have L/D ratios of this magnitude.

In another embodiment, the invention features a texturized fibrous material that includes a cellulosic or lignocellulosic material having internal fibers, where the cellulosic or lignocellulosic material is sheared to the extent that the internal fibers are substantially exposed.

The texturized fibrous material can, for example, be incorporated into (e.g., associated with, blended with, adjacent to, surrounded by, or within) a structure or carrier (e.g., a netting, a membrane, a flotation device, a bag, a shell, or a biodegradable substance). Optionally, the structure or carrier may itself be made from a texturized fibrous material (e.g., a texturized fibrous material of the invention), or of a composition or composite of a texturized fibrous material.

The texturized fibrous material can have a bulk density less than about 0.5 grams per cubic centimeter (g/cm³), or even less than about 0.2 g/cm³.

Compositions that include the texturized fibrous materials described above, together with a chemical or chemical formulation (e.g., a pharmaceutical such as an antibiotic or contraceptive, optionally with an excipient; an agricultural compound such as a fertilizer, herbicide, or pesticide; or a formulation that includes enzymes) are also within the scope of the invention, as are compositions that include the texturized fibrous materials and other liquid or solid ingredients (e.g., particulate, powdered, or granulated solids such as plant seed, foodstuffs, or bacteria).

Composites that include thermoplastic resin and the texturized fibrous materials are also contemplated. The resin

2

can be, for example, polyethylene, polypropylene, polystyrene, polycarbonate, polybutylene, a thermoplastic polyester, a polyether, a thermoplastic polyurethane, polyvinylchloride, or a polyamide, or a combination of two or more resins.

In some cases, at least about 5% by weight (e.g., 5%, 10%, 25%, 50%, 75%, 90%, 95%, 99%, or about 100%) of the fibrous material included in the composites is texturized.

The composite may include, for example, about 30% to about 70% by weight resin and about 30% to about 70% by weight texturized fibrous material, although proportions outside of these ranges may also be used. The composites can be quite strong, in some cases having a flexural strength of at least about 6,000 to 10,000 psi.

The composites can also include inorganic additives such as calcium carbonate, graphite, asbestos, wollastonite, mica, glass, fiber glass, chalk, talc, silica, ceramic, ground construction waste, tire rubber powder, carbon fibers, or metal fibers (e.g., stainless steel or aluminum). The inorganic additives can represent about 0.5% to about 20% of the total weight of the composite.

The composite can be in the form of, for example, a pallet (e.g., an injection molded pallet), pipes, panels, decking materials, boards, housings, sheets, poles, straps, fencing, members, doors, shutters, awnings, shades, signs, frames, window casings, backboards, wallboards, flooring, tiles, railroad ties, forms, trays, tool handles, stalls, bedding, dispensers, staves, films, wraps, totes, barrels, boxes, packing materials, baskets, straps, slips, racks, casings, binders, dividers, walls, indoor and outdoor carpets, rugs, woven, and mats, frames, bookcases, sculptures, chairs, tables, desks, art, toys, games, wharves, piers, boats, masts, pollution control products, septic tanks, automotive panels, substrates, computer housings, above—and below-ground electrical casings, furniture, picnic tables, tents, playgrounds, benches, shelters, sporting goods, beds, bedpans, thread, filament, cloth, plaques, trays, hangers, servers, pools, insulation, caskets, bookcovers, clothes, canes, crutches, and other construction, agricultural, material handling, transportation, automotive, industrial, environmental, naval, electrical, electronic, recreational, medical, textile, and consumer products. The composites can also be in the form of a fiber, filament, or film.

The terms "texturized cellulosic or lignocellulosic material" and "texturized fibrous material" as used herein, mean that the cellulosic or lignocellulosic material has been sheared to the extent that its internal fibers are substantially exposed. At least about 50%, more preferably at least about 70%, of these fibers have a length/diameter (L/D) ratio of at least 5, more preferably at least 25, or at least 50. An example of texturized cellulosic material is shown in FIG. 1.

The texturized fibrous materials of the invention have properties that render them useful for various applications. For example, the texturized fibrous materials have absorbent properties, which can be exploited, for example, for pollution control. The fibers are generally biodegradable, making them suitable, for example, for drug or chemical delivery (e.g., in the treatment of humans, animals, or in agricultural applications). The texturized fibrous materials can also be used to reinforce polymeric resins.

Those composites that include texturized fibrous material and resin are strong, light-weight, and inexpensive. The raw materials used to make the composites are available as virgin or recycled materials; for example, they may include discarded containers composed of resins, and waste cellulosic or lignocellulosic fiber.

Other features and advantages of the invention will be apparent from the following detailed description, and from the claims.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a photograph of a texturized newspaper, magnified fifty times.

DETAILED DESCRIPTION OF THE INVENTION

Examples of cellulosic raw materials include paper and paper products such as newsprint and effluent from paper manufacture; examples of lignocellulosic raw materials include wood, wood fibers, and wood-related materials, as well as materials derived from kenaf, grasses, rice hulls, bagasse, cotton, jute, other stem plants (e.g., hemp, flax, bamboo; both bast and core fibers), leaf plants (e.g., sisal, abaca), and agricultural fibers (e.g., cereal straw, corn cobs, rice hulls, and coconut hair). Aside from virgin raw materials, post-consumer, industrial (e.g., offal), and processing waste (e.g., effluent) can also be used as fiber sources.

Preparation of Texturized Fibrous Material

If scrap cellulosic or lignocellulosic materials are used, they should be clean and dry. The raw material can be texturized using any one of a number of mechanical means, or combinations thereof. One method of texturizing includes first cutting the cellulosic or lignocellulosic material into 1/4- to 1/2-inch pieces, if necessary, using a standard cutting apparatus. Counter-rotating screw shredders and segmented rotating screw shredders such as those manufactured by Munson (Utica, N.Y.) can also be used, as can a standard document shredder as found in many offices.

The cellulosic or lignocellulosic material is then sheared with a rotary cutter, such as the one manufactured by Sprout, Waldron Companies, as described in Perry's Chem. Eng. Handbook, 6th Ed., at 8-29 (1984). Although other settings can be used, the spacing between the rotating knives and bed knives of the rotary cutter is typically set to 0.020" or less, and blade rotation is set to 750 rpm or more. The rotary cutter can be cooled to 100° C. or lower during the process, for example, using a water jacket.

The texturized material is passed through a discharge screen. Larger screens (e.g., up to 6 mm) can be used in large-scale production. The cellulosic or lignocellulosic feedstock is generally kept in contact with the blades of the rotary cutter until the fibers are pulled apart; smaller screens (e.g., 2 mm mesh) provide longer residence times and more complete texturization, but can result in lower length/diameter (L/D) aspect ratios. A vacuum drawer can be attached to the screen to maximize and maintain fiber length/diameter aspect ratio.

The texturized fibrous materials can be directly stored in sealed bags or may be dried at approximately 105° C. for 4-18 hours (e.g., until the moisture content is less than about 0.5%) immediately before use. FIG. 1 is an SEM photograph of texturized newspaper.

Alternative texturizing methods include stone grinding, mechanical ripping or tearing, and other methods whereby the material's internal fibers can be exposed (e.g., pin grinding, air attrition milling).

Uses of Texturized Fibrous Material

Texturized fibrous materials and compositions and composites of such fibers with other chemicals and chemical formulations can be prepared to take advantage of the material's properties. The materials can be used to absorb chemicals, for example, potentially absorbing many times their own weight. Thus, the materials could, for instance, be used to absorb spilled oil, or for clean-up of environmental pollution, for example, in water, in the air, or on land. Similarly, the material's absorbent properties, together with its biodegradability, also make them useful for delivery of chemicals or chemical formulations. For example, the mate-

rials can be treated with solutions of enzymes or pharmaceuticals such as antibiotics, nutrients, or contraceptives, and any necessary excipients, for drug delivery (e.g., for treatment of humans or animals, or for use as or in animal feed and/or bedding), as well as with solutions of fertilizers, herbicides, or pesticides. The materials can optionally be chemically treated to enhance a specific absorption property. For example, the materials can be treated with silanes to render them lipophilic.

Compositions including texturized materials combined with liquids or particulate, powdered, or granulated solids can also be prepared. For example, texturized materials can be blended with seeds (i.e., with or without treatment with a solution of fertilizer, pesticides, etc.), foodstuffs, or bacteria (e.g., bacteria that digest toxins). The ratio of fibrous materials to the other components of the compositions will depend on the nature of the components and readily be adjusted for a specific product application.

In some cases, it may be advantageous to associate the texturized fibrous materials, or compositions or composites of such materials, with a structure or carrier such as a netting, a membrane, a flotation device, a bag, a shell, or a biodegradable substance. Optionally, the structure of carrier may itself be made of a texturized fibrous material (e.g., a material of the invention), or a composition or composite thereof.

Composites of Texturized Fibrous Material and Resin

Texturized fibrous materials can also be combined with resins to form strong, lightweight composites. Materials that have been treated with chemicals or chemical formulations, as described above, can similarly be combined with biodegradable or non-biodegradable resins to form composites, allowing the introduction of, for example, hydrophilic substances into otherwise hydrophobic polymer matrices. Alternatively, the composites including texturized fibrous materials and resin can be treated with chemicals or chemical formulations.

The texturized cellulosic or lignocellulosic material provides the composite with strength. The composite may include from about 10% to about 90%, for example from about 30% to about 70%, of the texturized cellulosic or lignocellulosic material by weight.

The resin encapsulates the texturized cellulosic or lignocellulosic material in the composites, and helps control the shape of the composites. The resin also transfers external loads to the fibrous materials and protects the fiber from environmental and structural damage. Composites can include, for example, about 10% to about 90%, more preferably about 30% to about 70%, by weight, of the resin.

Examples of resins that are suitably combined with texturized fibers include polyethylene (including, e.g., low density polyethylene and high density polyethylene), polypropylene, polystyrene, polycarbonate, polybutylene, thermoplastic polyesters (e.g., PET), polyethers, thermoplastic polyurethane, PVC, polyamides (e.g., nylon) and other resins. It is preferred that the resins have a low melt flow index. Preferred resins include polyethylene and polypropylene with melt flow indices of less than 3 g/10 min, and more preferably less than 1 g/10 min.

The resins can be purchased as virgin material, or obtained as waste materials, and can be purchased in pelletized or granulated form. One source of waste resin is used polyethylene milk bottles. If surface moisture is present on the pelletized or granulated resin, however, it should be dried before use.

The composites can also include coupling agents. The coupling agents help to bond the hydrophilic fibers to the hydrophobic resins. Examples of coupling agents include maleic anhydride modified polyethylenes, such those in the FUSABOND® (available from Dupont, Delaware) and

POLYBOND® (available from Uniroyal Chemical, Connecticut) series. One suitable coupling agent is a maleic anhydride modified high density polyethylene such as FUSABOND® MB 100D.

The composites can also contain additives known to those in the art of compounding, such as plasticizers, lubricants, antioxidants, opacifiers, heat stabilizers, colorants, flame retardants, biocides, impact modifiers, photostabilizers, and antistatic agents.

The composites can also include inorganic additives such as calcium carbonate, graphite, asbestos, wollastonite, mica, glass, fiber glass, chalk, silica, talc, ceramic, ground construction waste, tire rubber powder, carbon fibers, or metal fibers (e.g., aluminum, stainless steel). When such additives are included, they are typically present in quantities of from about 0.5% up to about 20–30% by weight. For example, submicron calcium carbonate can be added to the composites of fiber and resin to improve impact modification characteristics or to enhance composite strength.

Preparation of Compositions

Compositions containing the texturized cellulosic or lignocellulosic materials and chemicals, chemical formulations, or other solids can be prepared, for example, in various immersion, spraying, or blending apparatuses, including, but not limited to, ribbon blenders, cone blenders, double cone blenders, and Patterson-Kelly "V" blenders.

For example, a composition containing 90% by weight texturized cellulosic or lignocellulosic material and 10% by weight ammonium phosphate or sodium bicarbonate can be prepared in a cone blender to create a fire-retardant material for absorbing oil.

Preparation of Composites of Texturized Fiber and Resin

Composites of texturized fibrous material and resin can be prepared as follows. A standard rubber/plastic compounding 2-roll mill is heated to 325–400° F. The resin (usually in the form of pellets or granules) is added to the heated roll mill. After about 5 to 10 minutes, the coupling agent is added to the roll mill. After another five minutes, the texturized cellulosic or lignocellulosic material is added to the molten resin/coupling agent mixture. The texturized material is added over a period of about 10 minutes.

The composite is removed from the roll mill, cut into sheets and allowed to cool to room temperature. It is then compression molded into plaques using standard compression molding techniques.

Alternatively, a mixer, such as a Banbury internal mixer, is charged with the ingredients. The ingredients are mixed, while the temperature is maintained at less than about 190° C. The mixture can then be compression molded.

In another embodiment, the ingredients can be mixed in an extruder mixer, such as a twin-screw extruder equipped with co-rotating screws. The resin and the coupling agent are introduced at the extruder feed throat; the texturized cellulosic or lignocellulosic material is introduced about 1/3 of the way down the length of the extruder into the molten resin. The internal temperature of the extruder is maintained at less than about 190° C. At the output, the composite can be, for example, pelletized by cold strand cutting.

Alternatively, the mixture can first be prepared in a mixer, then transferred to an extruder.

In another embodiment, the composite can be formed into fibers, using fiber-forming techniques known to those in the art, or into filaments for knitting, warping, weaving, braiding, or making non-wovens. In a further embodiment, the composite can be made into a film.

Properties of the Composites of Texturized Fibrous Material and Resin

The resulting composites include a network of fibers, encapsulated within a resin matrix. The fibers form a lattice network, which provides the composite with strength. Since the cellulosic or lignocellulosic material is texturized, the amount of surface area available to bond to the resin is increased, in comparison to composites prepared with un-texturized cellulosic or lignocellulosic material. The resin binds to the surfaces of the exposed fibers, creating an intimate blend of the fiber network and the resin matrix. The intimate blending of the fibers and the resin matrix further strengthens the composites.

Uses of the Composites of Texturized Fibrous Material and Resin

The resin/fibrous material composites can be used in a number of applications. The composites are strong and light weight; they can be used, for example, as wood substitutes. The resin coating renders the composites water-resistant, so they may be used in outdoor applications. For example, the composites may be used to make pallets, which are often stored outdoors for extended periods of time, wine staves, rowboats, furniture, skis, and oars. Many other uses are contemplated, including panels, pipes, decking materials, boards, housings, sheets, poles, straps, fencing, members, doors, shutters, awnings, shades, signs, frames, window casings, backboards, wallboards, flooring, tiles, railroad ties, forms, trays, tool handles, stalls, bedding, dispensers, staves, films, wraps, totes, barrels, boxes, packing materials, baskets, straps, slips, racks, casings, binders, dividers, walls, indoor and outdoor carpets, rugs, wovens, and mats, frames, bookcases, sculptures, chairs, tables, desks, art, toys, games, wharves, piers, boats, masts, pollution control products, septic tanks, automotive panels, substrates, computer housings, above- and below-ground electrical casings, furniture, picnic tables, tents, playgrounds, benches, shelters, sporting goods, beds, bedpans, thread, filament, cloth, plaques, trays, hangers, servers, pools, insulation, caskets, bookcovers, clothes, canes, crutches, and other construction, agricultural, material handling, transportation, automotive, industrial, environmental, naval, electrical, electronic, recreational, medical, textile, and consumer products. Numerous other applications are also envisioned. The composites may also be used, for example, as the base or carcass for a veneer product. Moreover, the composites can be, for example, surface treated, grooved, milled, shaped, imprinted, textured, compressed, punched, or colored. The surface of the composites can be smooth or rough.

The following examples illustrate certain embodiments and aspects of the present invention and not to be construed as limiting the scope thereof.

EXAMPLES

Example 1

A 1500 pound skid of virgin, half-gallon juice cartons made of polycoated white kraft board was obtained from International Paper. Each carton was folded flat.

The cartons were fed into a 3 hp Flinch Baugh shredder at a rate of approximately 15 to 20 pounds per hour. The shredder was equipped with two rotary blades, each 12" in length, two fixed blades, and a 0.3" discharge screen. The gap between the rotary and fixed blades was 0.10".

The output from the shredder, consisting primarily of confetti-like pieces, about 0.1" to 0.5" in width and about 0.25" to 1" in length, was then fed into a Thomas Wiley Mill Model 2D5 rotary cutter. The rotary cutter had four rotary blades, four fixed blades, and a 2 mm discharge screen. Each blade was approximately 2" long. The blade gap was set at 0.020".

7

The rotary cutter sheared the confetti-like pieces across the knife edges, tearing the pieces apart and releasing a finely texturized fiber at a rate of about one pound per hour. The fiber had an average minimum L/D ratio of between five and 100 or more. The bulk density of the texturized fiber was on the order of 0.1 g/cc.

Example 2

Composites of texturized fiber and resin were prepared as follows. A standard rubber/plastic compounding 2-roll mill was heated to 325–400° F. The resin (usually in the form of pellets or granules) was added to the heated roll mill. After about 5 to 10 minutes, the resin banded on the rolls (i.e., it melted and fused on the rolls). The coupling agent was then added to the roll mill. After another five minutes, the texturized cellulosic or lignocellulosic material was added to the molten resin/coupling agent mixture. The cellulosic or lignocellulosic fiber was added over a period of about 10 minutes.

The composite was then removed from the roll mill, cut into sheets, and allowed to cool to room temperature. Batches of about 80 g each were compression molded into 6"x6"x1/8" plaques using standard compression molding techniques.

One composition contained the following ingredients:

Composition No. 1	
Ingredient	Amount (g)
High density polyethylene ¹	160
Old newspaper ²	240
Coupling agent ³	8

¹Marlex 16007

²Texturized using rotary cutter with 2 mm mesh

³FUSABOND ® 100D

The plaques were machined into appropriate test specimens and tested according to the procedures outlined in the method specified. Three different specimens were tested for each property, and the mean value for each test was calculated. The properties of Composition No. 1 are as follows:

Flexural strength (10 ³ psi)	9.81 (ASTM D790)
Flexural modulus (10 ⁵ psi)	6.27 (ASTM D790)

A second composition contains the following ingredients:

Composition No. 2	
Ingredient	Amount (g)
High density polyethylene ¹	160
Old magazines ²	240
Coupling agent ³	8
The properties of Composition No. 2 are as follows:	
Flexural strength (10 ³ psi)	9.06 (ASTM D790)
Flexural modulus (10 ⁵ psi)	6.78 (ASTM D790)

8

A third composition contains the following ingredients:

Composition No. 3	
Ingredient	Amount (g)
HDPE ¹	160
Fiber paper ²	216
3.1 mm texturized kenaf	24
Coupling agent ³	8
The properties of Composition No. 3 are as follows:	
Flexural strength (10 ³ psi)	11.4 (ASTM D790)
Flexural modulus (10 ⁵ psi)	6.41 (ASTM D790)

A fourth composition contains the following ingredients:

Composition No. 4	
Ingredient	Amount (g)
SUPERFLEX™ CaCO ₃	33
Fiber ^{2,4}	67
HDPE (w/3% compatibilizer) ^{1,3}	100
The properties of Composition No. 4 are as follows:	
Flexural strength (10 ³ psi)	8.29 (ASTM D790)
Ultimate elongation (%)	<5 (ASTM D638)
Flexural modulus (10 ⁵ psi)	10.1 (ASTM D790)
Notch Izod (ft-lb/in)	1.39 (ASTM D256-97)

⁴Virgin polycoated milk cartons

A fifth composition contains the following ingredients:

Composition No. 5	
Ingredient	Amount (parts)
SUPERFLEX™ CaCO ₃	22
Fiber ^{2,4}	67
HDPE (w/3% compatibilizer) ^{1,3}	100
The properties of Composition No. 5 are as follows:	
Flexural strength (10 ³ psi)	8.38 (ASTM D790)
Ultimate elongation (%)	<5 (ASTM D638)
Flexural modulus (10 ⁵ psi)	9.86 (ASTM D790)
Notch Izod (ft-lb/in)	1.37 (ASTM D256-97)

A sixth composition contains the following ingredients:

Composition No. 6	
Ingredient	Amount (parts)
ULTRAFLEX™ CaCO ₃	33
Fiber ^{2,4}	67
HDPE/compatibilizer ^{1,3}	100
The properties of Composition No. 6 are as follows:	
Flexural strength (10 ³ psi)	7.43 (ASTM D790)
Ultimate elongation (%)	<5 (ASTM D638)
Flexural modulus (10 ⁵ psi)	11.6 (ASTM D790)
Notch Izod (ft-lb/in)	1.27 (ASTM D256-97)

A seventh composition contains the following ingredients:

Composition No. 7	
Ingredient	Amount (pbw)
HDPE (w/3% compatibilizer) ^{3,5}	60
Kraftboard ²	40
The properties of Composition No. 7 are as follows:	
Flexural Strength (10 ³ psi)	7.79 (ASTM D790)
Ultimate elongation (%)	<5 (ASTM D638)
Flexural Modulus (10 ³ psi)	7.19 (ASTM D790)

⁵HDPE with melt-flow index <1

other embodiments are within the claims.

What is claimed is:

1. A process for preparing a texturized fibrous material, the process comprising:
 - shearing a cellulosic or lignocellulosic material having internal fibers, to the extent that the internal fibers are substantially exposed, resulting in texturized fibrous material.
2. The method of claim 1, wherein said cellulosic or lignocellulosic material is selected from the group consisting of flax, hemp, cotton, jute, rags, paper, paper products, and byproducts of paper manufacturing.
3. The method of claim 1, wherein the cellulosic or lignocellulosic material is pulp board.
4. The method of claim 1, wherein the cellulosic or lignocellulosic material is a synthetic material.
5. The method of claim 1, wherein the cellulosic or lignocellulosic material is a non-woven material.
6. The method of claim 1, wherein at least about 50% of the fibers have a length/diameter ratio of at least about 5.
7. The method of claim 1, wherein at least about 50% of the fibers have a length/diameter ratio of at least about 25.
8. The method of claim 1, wherein at least about 50% of the fibers have a length/diameter ratio of at least about 50.
9. A texturized fibrous material comprising a cellulosic or lignocellulosic material having internal fibers, wherein said cellulosic or lignocellulosic material is sheared to the extent that the internal fibers are substantially exposed.
10. The texturized fibrous material of claim 9, wherein said material is incorporated into a structure or carrier.
11. The texturized fibrous material of claim 10, wherein the structure or carrier also comprises a texturized fibrous material.
12. The texturized fibrous material of claim 9, wherein said texturized fibrous material has a bulk density less than about 0.5 grams per cubic centimeter.
13. The texturized fibrous material of claim 9, wherein said texturized fibrous material has a bulk density less than about 0.2 grams per cubic centimeter.
14. The texturized fibrous material of claim 9, wherein said cellulosic or lignocellulosic material comprises paper or paper products.
15. A composition comprising the texturized fiber of claim 9 and a chemical or chemical formulation.
16. The composition of claim 15, wherein the chemical formulation comprises a pharmaceutical.
17. The composition of claim 16, wherein the chemical formulation is an agricultural compound.
18. The composition of claim 15, wherein the chemical formulation comprises an enzyme.
19. A composition comprising the texturized fibrous material of claim 9 and a liquid.
20. A composition comprising the texturized fiber of claim 9 and particulate, powdered, or granulated solid.

21. The composition of claim 20, wherein the solid comprises plant seed.

22. The composition of claim 20, wherein the solid comprises a foodstuff.

23. The composition of claim 20, wherein the solid comprises bacteria.

24. A composite comprising thermoplastic resin and the texturized fibrous material of claim 9, wherein:

the resin is selected from the group consisting of polyethylene, polypropylene, polystyrene, polycarbonate, polybutylene, thermoplastic polyesters, polyethers, thermoplastic polyurethane, polyvinylchloride, and polyamides.

25. The composite of claim 24, wherein at least about 5% by weight of the cellulosic or lignocellulosic material is texturized.

26. The composite of claim 24, wherein the resin is polyethylene.

27. The composite of claim 24, wherein the resin is polypropylene.

28. The composite of claim 24, wherein the composite comprises about 30% to about 70% by weight resin and about 30% to about 70% by weight texturized fibrous material.

29. The composite of claim 24, wherein the composite has a flexural strength of at least 6,000 psi.

30. The composite of claim 24, wherein the composite has a flexural strength of at least 10,000 psi.

31. The composite of claim 24, further comprising an inorganic additive.

32. The composite of claim 31, wherein the inorganic additive is selected from the group consisting of calcium carbonate, graphite, asbestos, wollastonite, mica, glass, fiber glass, chalk, talc, silica, ceramic, ground construction waste, tire rubber powder, carbon fibers, and metal fibers.

33. The composite of claim 31, wherein the inorganic additive comprises from about 0.5% to about 20% of the total weight of the composite.

34. The composite of claim 24, wherein said composite is in the form of a pallet.

35. The composite of claim 34, wherein said pallet is injection molded.

36. The composite of claim 24, wherein said composite is in the form of an article selected from the group consisting of panels, pipes, decking materials, boards, housings, sheets, poles, straps, fencing, members, doors, shutters, awnings, shades, signs, frames, window casings, backboards, wallboards, flooring, tiles, railroad ties, forms, trays, tool handles, stalls, bedding, dispensers, staves, films, wraps, totes, barrels, boxes, packing materials, baskets, straps, slips, racks, casings, binders, dividers, walls, indoor and outdoor carpets, rugs, wovens, and mats, frames, bookcases, sculptures, chairs, tables, desks, art, toys, games, wharves, piers, boats, masts, pollution control products, septic tanks, automotive panels, substrates, computer housings, above- and below-ground electrical casings, furniture, picnic tables, tents, playgrounds, benches, shelters, sporting goods, beds, bedpans, thread, filament, cloth, plaques, trays, hangers, servers, pools, insulation, caskets, bookcovers, clothes, canes, crutches, and other construction, agricultural, material handling, transportation, automotive, industrial, environmental, naval, electrical, electronic, recreational, medical, textile, and consumer products.

37. The composite of claim 24, wherein said composite is in the form of a fiber, filament, or film.

* * * * *